

## User Guideline

### Ultracur3D® EPD 2006

The following User guideline is for professionals who use: **Ultracur3D® EPD 2006**.

The safety data given in this publication is for information purposes only and does not constitute a legally binding Material Safety Data Sheet (MSDS). The relevant MSDS can be obtained upon request from your supplier or you may contact Forward AM directly at [sales@forward-am.com](mailto:sales@forward-am.com).

**For more information, please refer to the country specific MSDS for advice.**

#### Manufacturer

Forward AM Technologies GmbH

69115 Heidelberg

GERMANY

E-mail address: [sales@forward-am.com](mailto:sales@forward-am.com)

<http://www.forward-am.com/>

#### Storage Conditions and Disposal Considerations

Keep container tightly closed in a room temperature, well-ventilated place. Keep container dry. If Material is not being used fill it back through a filter in the corresponding material bottle. The filter prevents to fill cured pieces or failed prints back into the bottle. Ultracur3D® EPD 2006 must be disposed of or incinerated in accordance with local regulations.

**For more information, please refer to the country specific MSDS for advice.**

#### Delivery units

Ultracur3D® EPD 2006 is available in the following packaging sizes: 5 kg, 10 kg and possible larger volume packaging are also available upon request.

#### Intended Use

Ultracur3D® EPD 2006 is a technical material based on (meth-)acrylate resin for suggested Photocentric LCD systems. Working wavelength: 460 nm. Attached a list of suggested 3D printer and Printing parameters. For more information contact Forward AM directly at [sales@forward-am.com](mailto:sales@forward-am.com).

## Example of Suitable 3D-Printers and Settings

Printer	Photocentric Magna	Photocentric Magna
Wavelength	460 nm	460 nm
Curing time	8 s	16 s
Voxel depth	100 $\mu$ m	250 $\mu$ m

Detailed printing parameter can be found on **Photocentric studio**.

## Printing Process

**Preparation of Resin**

The material should be processed at room temperature. Before usage the material should be shaken well. Pour it slowly in the vat and wait a couple minutes, until smooth, bubble-free surface is obtained before starting the print job.



**Removing parts**

As the suitable 3D printer example and setting parameter stated above are only for general guidance purpose, user can get the latest settings via Photocentric studio. Please refer to Instruction of Use or User Guide of the employed 3D-Printer for the printer settings and handling.

## Cleaning and Post curing process

### Cleaning

Ultracur3D® EPD 2006 can be cleaned with Ultracur3D® Cleaner & tap water, please refer to the following cleaning procedure.

#### Cleaning with Resin cleaner & water

- Step 1: Place the platform in Ultrasonic bath Wash 99 filled with Resin cleaner. Run the bath for 2 intervals of 8 minutes each.
- Step 2: Do not remove the parts from the platform. Place the platform in Ultrasonic bath Wash 99/Air Wash L filled with Water. Run the bath for 8 minutes.
- Step 3: Do not remove the parts from the platform. Place the parts in Cure L / Cure L 2 for post curing.

Ultracur3D® EPD 2006 parts require adequate post curing to achieve the optimized final mechanical properties.

#### Example of Post curing procedure

Post-curing unit	Photocentric Cure L / Cure L 2	Dymax ECE 2000 flood
Amount of cycles	3	2
Duration of one curing cycle	60 minutes	15 minutes
Temperature	65°C	Not applicable

### Post curing

### Finishing Process

Remove the parts from the platform once the post curing cycles have been finished. Once you have removed the parts from the platform, support structures can be removed carefully, and the surface can be smoothed if necessary. Now the parts are ready to use.

These proceedings are only general guidelines, the optimal printing settings as well as curing time must be defined by the user himself. The post-curing might differ by using different 3D-Printers and different post-curing units may require different settings.

*The data contained in this publication are based on our current knowledge and experience. They do not constitute an agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. The customer and/or user is responsible to consider and respect all hazard and safety issues according to the MSDS of Ultracur3D® EPD 2006 and take, implement and/or install adequate measures and precautions to avoid any personal injuries, property damages and/or environmental pollution. Therefore, Forward AM Technologies GmbH shall not be liable for any personal injury, property damages and/or environmental emissions arising out of or related to the testing, handling or usage, storage and possession of Ultracur3D® EPD 2006. It is the sole responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed (02/2020)*

**Forward AM Technologies GmbH** [sales@forward-am.com](mailto:sales@forward-am.com) [www.forward-am.com](http://www.forward-am.com)

**Photocentric**

UK - Cambridge House, Oxney Road, Peterborough, PE1 5YW. +44 1733 349937. info@photocentric.co.uk  
USA - 2205 West Parkside Lane, Phoenix, 85027, AZ. (623) 581-3220. info@photocentricusa.com