

# Ultracur3D<sup>®</sup> DM 2505

## User Guideline



## INTRODUCTION

The following user guideline is for professionals who use: Ultracur3D<sup>®</sup> DM 2505.

The safety data given in this publication is for information purposes only and does not constitute a legally binding Material Safety Data Sheet (MSDS). The relevant MSDS can be obtained upon request from your supplier or you may contact BASF directly at [sales@basf-3dps.com](mailto:sales@basf-3dps.com).

**For more information, please refer to the country specific MSDS for advice.**

## STORAGE CONDITIONS AND DISPOSAL CONSIDERATIONS

Keep container tightly closed in a room temperature, well-ventilated place. Keep container dry. If material is not being used, fill it back through a filter in the corresponding material bottle. The filter prevents cured pieces or failed prints from going back into the bottle. Ultracur3D<sup>®</sup> DM 2505 must be disposed of in accordance with local regulations.

**For more information, please refer to the country specific MSDS for advice.**

## INTENDED USE

Ultracur3D® DM 2505 is a technical material based on (meth-)acrylate resin for suggested LCD and DLP systems. Working wavelength: 385 nm or 405 nm. Below, you can find some suggested 3D printers and printing parameters. For more information contact BASF directly at [sales@basf-3dps.com](mailto:sales@basf-3dps.com).

## EXAMPLES OF SUITABLE 3D-PRINTERS AND SETTINGS

	Wavelength	Power	Curing time	Voxel depth
<b>Creality Halot Sky CL 89</b>	405 nm	2 mW / cm <sup>2</sup>	7 s	100 µm
<b>MiiCraft Ultra 125</b>	405 nm	4 mW / cm <sup>2</sup>	3.5 s	100 µm
<b>MiiCraft Ultra 125 Y</b>	385 nm	4 mW / cm <sup>2</sup>	3.5 s	100 µm
<b>Rapidshape i30+®</b>	385 nm	2 mW / cm <sup>2</sup>	5 s	100 µm
<b>Stratasys Origin One</b>	385 nm	5 mW / cm <sup>2</sup>	3.25 s	100 µm

If you cannot find your printer in the table, you can use the values below as starting parameters. These are only approximations, different 3D printers may require different curing times and further optimization, but these values should be a good starting point.

The given values are all for printing at a layer thickness / voxel depth of 100 µm. If you need starting parameters for a different layer thickness, please contact us.

### 405 nm Wavelength 3D Printer

<b>Power*</b>	5 mW / cm <sup>2</sup>	4 mW / cm <sup>2</sup>	3 mW / cm <sup>2</sup>	2 mW / cm <sup>2</sup>
<b>Suggested curing time</b>	3.6 s	4.5 s	6 s	9 s

### 385 nm Wavelength 3D Printer

<b>Power*</b>	5 mW / cm <sup>2</sup>	4 mW / cm <sup>2</sup>	3 mW / cm <sup>2</sup>	2 mW / cm <sup>2</sup>
<b>Suggested curing time</b>	4.6 s	5.8 s	7.8 s	11.7 s

\* Power measured directly on the glass

## DESIGN INFORMATION

For designing the dental model and the mold for thermoforming, we recommend using only certified Software. If the model is hollow, make sure to have drainage channels (if no platform with holes is used) to make sure that the material is not trapped inside. For some hollow models, support structures might be needed. We recommend printing horizontal and always with a connector.

## PRINTING PROCESS

The material should be processed at room temperature. Ultracur3D® DM 2505 has a high pigment loading and therefore needs very thorough mixing before starting any print jobs. Color deviations or failed prints may occur when the material is not mixed properly. If regular shaking of the bottle doesn't work, we recommend rolling the material on a bottle roller with ceramic balls (e.g. 15-20mm Al<sub>2</sub>O<sub>3</sub> balls) inside the bottle for 30-60 minutes. Pour it slowly in the vat and wait a couple of minutes, until the bubbles are gone before starting the print job.

The 3D printer examples and settings stated above are only for general guidance. The fully optimized settings should always be determined by the users themselves, according to their specific needs. Please always refer to the user manual of the employed 3D printer for instructions on printer settings and handling.

Remove the parts carefully from the build platform with a suitable tool, for more information, refer to the user manual of the used 3D printer.

## CLEANING AND POST CURING PROCESS

Ultracur3D® DM 2505 can be cleaned with water (preferably distilled or purified), please refer to the following cleaning procedure.

### Cleaning with water (preferably distilled or purified)

- Step 1: Place the parts in a container filled with water and place this container in an Ultrasonic bath filled with water for 4 minutes. The cleaning time can vary depending on the complexity of the printed geometry.
- Step 2: Rinse the parts with water for a few seconds. Fine structures or holes may be better cleaned by using water and a syringe or by separate brushing. Next, place the parts in a container filled with fresh water and place this container in an Ultrasonic bath filled with water for 4 minutes.
- Step 3: Blow dry the parts with pressurized air or nitrogen, until the parts are clean.
- Remark: Even though water is used for the cleaning, this water will contain photopolymer traces after use and should be handled according to local regulations for chemical waste. Please refer to the MSDS.
- Step 4: Place the parts into a warming cabinet at 40°C for 30 minutes to dry off any remaining cleaning solvent.
- Remark: Having a proper drying step for this material is important, otherwise some surface discoloration can happen.

## EXAMPLES OF POST CURING PROCEDURES

Ultracur3D® DM 2505 parts require adequate post-curing to achieve the optimal mechanical properties. After each post-curing cycle, the parts need to be flipped to achieve an even curing. After post-curing, remove any support structures and smoothen the surface if required.

	UV lamp	Power in mW / cm <sup>2</sup>	Duration of post-curing	Notes
Dymax ECE 2000 flood	Hg Metal Halide Bulb (broad spectrum)	Ca. 140 mW / cm <sup>2</sup> at 405 nm	2 x 300 seconds	Shelf height K
OtoFlash G 171	Flash-bulbs (broad spectrum)	Ca. 3.5 mW / cm <sup>2</sup> at 405 nm	2 x 2000 flashes	With Nitrogen
Zortrax Curing Station	405 nm LED	Ca. 35 mW / cm <sup>2</sup> at 405 nm	2 x 10 minutes	

These proceedings are only general guidelines. In the end, the user has to determine the optimum post-curing procedure based on their specific requirements and the equipment used.

---

*The data contained in this publication are based on our current knowledge and experience. They do not constitute an agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. The customer and/or user is responsible to consider and respect all hazard and safety issues according to the MSDS of Ultracur3D® DM 2505 and take, implement and/or install adequate measures and precautions to avoid any personal injuries, property damages and/or environmental pollution. Therefore, BASF3D Printing Solutions GmbH shall not be liable for any personal injury, property damages and/or environmental emissions arising out of or related to the testing, handling or usage, storage and possession of Ultracur3D® DM 2505. It is the sole responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed (02/2020)*