

Asiga - Max UV 385

3D Printing Workflow: Ultracur3D® RG 3280

Technology: DLP

PRINT SETTINGS

Layer Thickness (µm)	Irradiance (mW/cm ²)	Exposure Time (s)
100	4,6	1,7

	WASH CYCLE 1	WASH CYCLE 2
Agitation Method	Rotor / Propeller	Rotor / Propeller
Cleaner	IPA	IPA
Cleaning Time (min)	1	1



WAIT BEFORE POST CURING

Waiting Time (min) None Temperature (°C) None

POST CURING

Model	Formcure
Settings	N.A.
Atmosphere	Ambient
Time (min) or Flashes	120
Flip & Repeat	No

THERMAL TREATMENT

Ramp up (°C / min)	1
Holding Temp. (°C)	150
Holding Time (h)	3
Ramp down (°C / min)	1