



Crealty - Halot Sky

3D Printing Workflow: Ultracur3D® DM 2505

Technology: LCD

PRINT SETTINGS

Layer Thickness (µm)	Irradiance (mW/cm2)	Exposure Time (s)
100	2	7

WASH CYCLE 1

WASH CYCLE 2

Agitation Method	Ultrasonic	Ultrasonic
Cleaner	Ultracur3D® Cleaner	IPA
Cleaning Time (min)	4	4



WAIT BEFORE POST CURING

Waiting Time (min) 30 Temperature (°C) 40

POST CURING

THERMAL TREATMENT

Model	Dymax ECE 2000	Ramp up (°C / min)	N.A.
Settings	N.A.	Holding Temp. (°C)	N.A.
Atmosphere	Ambient	Holding Time (h)	N.A.
Time (min) or Flashes	3	Ramp down (°C / min)	N.A.
Flip & Repeat	Yes		

Workflow N.: 2024-LFS-WF-0154