

forwardam.

Ultracur3D® ST 80 B
Tough | Economic | Black

Extended TDS

Complete Technical Documentation
and Testing Summary

Version 1.1

Contents

Technical Data Sheet 3

Biocompatibility..... 5

Are you looking for an updated TDS version? [Check out the latest online version here.](#)

Technical Data Sheet

Multi-purpose resin targeting the lowest cost per part.

The data contained in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, this data does not relieve processors from carrying out their own investigations and tests; neither does this data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose.

Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

The safety data given in this publication is for informational purposes only and does not constitute a legally binding MSDS. The relevant MSDS can be obtained upon request from your supplier or you may contact Forward AM Technologies GmbH directly at sales@forward-am.com.

General Properties	Method	Typical Values
Appearance	-	Black
Viscosity, 25°C	Cone/Plate Rheometer ¹⁾	620 mPas
Viscosity, 30°C	Cone/Plate Rheometer ¹⁾	440 mPas
Density (Printed Part)	ASTM D792	1.2 g/cm ³
Density (Liquid Resin)	ASTM D4052-18a	1.1 g/cm ³

Tensile Properties ²⁾	Method	Typical Values
E Modulus	ASTM D638	1650 MPa
Ultimate Tensile Strength	ASTM D638	35 MPa
Elongation at Break	ASTM D638	25%

Flexural Properties	Method	Typical Values
Flexural Modulus	ASTM D790	1550 MPa
Flexural Strength	ASTM D790	66 MPa

Impact Properties	Method	Typical Values
Notched Izod (Machined), 23°C	ASTM D256	22 J/m
Unnotched Izod, 23°C	ASTM D4812	727 J/m
Notched Charpy (Machined), 23°C	ISO 179-1	2.3 kJ/m ²

Thermal Properties	Method	Typical Values
HDT at 0.45 MPa	ASTM D648	52°C
HDT at 1.82 MPa	ASTM D648	44°C

Biocompatibility	Method	Typical Values
Cytotoxicity – Neutral Red	EN ISO 10993-5 (2009)	PASS ³⁾

Other	Method	Typical Values
Hardness Shore D	ASTM D2240	77

Mechanical properties overview

- 1) Determined with TA-Instrument DHR rheometer, cone/plate, diameter 60 mm, shear rate 100 s⁻¹
- 2) Tensile type ASTM D638 type IV, Pulling speed 5 mm/min
- 3) For the statement on Biocompatibility data see Chapter: [Biocompatibility](#)
- 4) If not noted otherwise, all specimens are 3D printed. Samples were tested at room temperature, 23°C. ASTM sample size (L x W x H): ASTM D790 80 x 4 x 10 mm, ASTM D256 63 x 3.2 x 12 mm, ASTM D648 127 x 3.2 x 13 mm, ISO 179-1 80 x 4 x 10 mm

The data contained in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, this data does not relieve processors from carrying out their own investigations and tests; neither does this data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose.

Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

The safety data given in this publication is for informational purposes only and does not constitute a legally binding MSDS. The relevant MSDS can be obtained upon request from your supplier or you may contact Forward AM Technologies GmbH directly at sales@forward-am.com.

Biocompatibility

Product: Ultracur3D® ST 80 B

Revision: 08th of December 2021

3D printed test items of the above stated product have fulfilled the requirements of tests as stated below:

Cytotoxicity Testing- Neutral red:

(EN ISO 10993-5 (2009))

The biocompatibility tests were recorded on test specimen of the referenced product to show compatibility of the material in general. The biocompatibility tests listed are not part of any continuous production protocol. The test assessments reflect only the test specimen and have to be retested on the final product. It remains the responsibility of the de-vice manufacturers and /or end-users to determine the suitability of all printed parts for their respective application.

For notice:

We give no warranties, expressed or implied, concerning the suitability of mentioned product for use in any medical device and pharmaceutical applications.

All information contained in this document is given in good faith and is based on sources believed to be reliable and accurate at the date of publication of this document.

It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

The certificate is exclusively for our customers and respective competent authorities. It is not intended for publication either in printed or electronic form (e.g. via Internet) by others. Thus, neither partial nor full publication is allowed without written permission. This product information was generated electronically and is valid without signature.